

## Description

ASC 1QS is a quick set acrylic coating for use over a variety of substrates. ASC 1QS provides resistance to early wash-off associated with heavy dew and light rain. The unique formulation of the ASC 1QS meets requirements for critical properties such as tensile strength, elongation, wet adhesion and weatherability.

Read and follow directions carefully. Refer to Material Safety Data Sheet for proper handling.

## Preparation

Surfaces must be cleaned, dried, and free of moisture on and beneath the surface. Remove dust, dirt, oil, loose granules and any other foreign contaminants. Surfaces with mildew growth should be cleaned with a bleach solution then rinsed thoroughly. Rusted metal should be cleaned with a wire brush. Pressure washing surface is recommended for best results. It is recommended to repair all holes, leaks and cracks with ASC 7 Elastomagic Cement and ASC F Polyester Fabric in the Three Course Installation Method.

Acceptance of the substrate is the sole decision of the owner or appointed representative.

## Application

For exterior use only. Protective clothing and eyewear should be used during application of this product. Apply on warm, sunny day preferably in the morning to provide maximum cure time. ASC 1QS must be applied to a dry surface. Prior to application water must be swept out of all puddles, waterways, and birdbaths. Temperature should be 55°F and rising.

Stir thoroughly before application to achieve a uniform consistency. Apply with a heavy-duty paint roller or professional spray equipment. Apply first coat at a rate of 1.5 gallons per square. Allow a minimum of 4 hours to dry. Apply second coat in cross hatch fashion at a rate of 1.5 gallons per square. Allow at least four hours between coats and 24-48 hours for full cure, dependent upon weather conditions. Relative humidity will directly affect drying/curing time.

## Cleanup

Clean tools with soap and warm water.

VOC/VOS 19.2 g/l max (0.16 lbs/gal)

## Chemical Ingredients

Water	CAS# 7732-18-5
Acrylic Copolymer	CAS# MIXTURE
Titanium Dioxide	CAS# 13463-67-7
Calcium Carbonate	CAS# 1317-65-3
Zinc Dioxide	CAS# 131413-2

## Precautions

DO NOT STORE AT TEMPERATURES BELOW 50°F (10°C) OR ABOVE 120°F (49°C). DO NOT ALLOW TO FREEZE. DO NOT APPLY WHEN HEAVY DEW OR RAIN IS EXPECTED WITHIN 24 HOURS. DO NOT THIN. When transporting this product, be sure the lid is tight and the pail is secured. Do not allow pail to tumble as this may loosen the lid and cause leakage or spillage.

Drying time may vary depending upon wet film thickness, temperature, humidity and air movement.

## CAUTION


KEEP OUT OF REACH OF CHILDREN. Close container after each use. HARMFUL OR FATAL IF SWALLOWED. EYE, SKIN, AND RESPIRATORY IRRITANT. USE WITH ADEQUATE VENTILATION. If swallowed do not induce vomiting. Call physician immediately. In case of eye contact- flush with large amounts of room temperature water for 15 minutes, skin contact- wash thoroughly with soap and water. Irregular or stopped breathing administer oxygen, give artificial respiration. Get immediate medical attention. Avoid prolonged breathing of vapor or spray mist.

CALIF PROP 65- CHEMICAL WARNING (CALIFORNIA HEALTH AND SAFETY CODE #25249.5 ET SEQ) WARNING: This product contains chemicals known to the State of California to cause cancer, birth defects or reproductive harm. Use proper protection and adequate ventilation when using product.

For Further information and advice regarding transportation, handling, storage, and disposal of chemical products, users should refer to the actual Material Safety Data Sheet containing physical, ecological, toxicological, and other safety related data. It is highly recommended to read the actual Material Safety Data Sheet before using the product.

## WARRANTY AND DISCLAIMER

American Standard Coatings warrants to the original purchaser that this product is free from any manufacturing defects that will materially affect the products performance for a period of one year. In the event there is a failure associated with a manufacturing defect of this product, American Standard Coatings shall, at its own discretion, provide the appropriate replacement product(s) or pay for the cost of the defective product only. There is no warranty for labor or installation costs of any kind. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. AMERICAN STANDARD COATINGS SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. To the best of our knowledge, the technical data contained herein is true and accurate at the date of issuance and is subject to change without prior notice. Contact American Standard Coatings prior to ordering for the most recent and up to date data sheet. For additional limited warranty and disclaimer information contact the American Standard Coatings corporate office at 562-777-8200.

	<b>Rated Product ID #: 1202-0001</b>		
		<b>Initial</b>	<b>Aged</b>
	<b>Solar Reflectance</b>	<b>0.88</b>	<b>0.74</b>
	<b>Thermal Emittance</b>	<b>0.90</b>	<b>0.91</b>
<small>The ratings above are subject to CRRC rating program conditions, requirements, and limitations. Visit <a href="http://coolroofs.org">coolroofs.org</a> for important information and disclaimers about CRRC rating conditions, requirements, and limitations.</small>			

## ASC 1QS Quick-Set Acrylic Coating



Available Colors:

White / CA Tan / CA Gray / Standard Tan / Standard Gray / Custom

Packaging:  
5 gallon pail  
55 gallon drum  
275 gallon tote