



Application:

In the area of the concrete wall- Apply first coat of ASC 11 Concrete Sealer at a rate of 1 gallon per square. Allow to properly cure. Apply first coat of ASC 1 Elastomeric Reflective Coating at a rate of 1.5 gallons per square. Allow a minimum of 4 hours to dry. Apply second coat, perpendicular to the first coat, in a cross hatch fashion at a rate of 1.5 gallons per square. Allow at least four hours between coats.

Concrete Wall Detail



Issue Date:
07/02/19

Not To Scale

Detail No.
ASC-TD-0110