



Application:

Apply 3 Gallons of ASC 1 at approximate rate of 3 gallons per 100 sq. feet, embed ASC F (polyester fabric). Apply 3 Gallons of ASC 1 at approximate rate of 3 gallons per 100 sq. feet in two passes of 1.5 gallons per pass. Roof to Wall Cant area as needed – Apply first coat of ASC 7 Elastomagic Cement with brush or trowel at 1/8-1/4 inch thickness. Immediately following embed ASC F Polyester Fabric. Lightly brush the polyester fabric into ASC 7 to achieve full saturation, smoothing out wrinkles or voids. Apply second coat of ASC 7 Elastomagic Cement.

Existing Metal Cap in place - Apply first coat of ASC 7 Elastomagic Cement with brush or trowel at 1/8-1/4 inch thickness. Immediately following embed ASC F Polyester Fabric. Lightly brush the polyester fabric into ASC 7 to achieve full saturation, smoothing out wrinkles or voids. Apply second coat of ASC 7 Elastomagic Cement. The area of coverage is interior edge of Metal Cap.

Wall Flashing With Metal Cap



Issue Date:
07/02/19

Not To Scale

Detail No.
ASC-TD-0118